



**SUBSTITUTE SPECIFICATION & ABSTRACT  
(Marked-up Version)**

**For U.S. Patent Application -  
Daisuke SAKURAI et al.  
(Serial No. 10/694,347)**

## SPECIFICATION

### TITLE OF THE INVENTION

MANUFACTURING METHOD FOR ELECTRONIC COMPONENT-  
MOUNTED COMPONENT, MANUFACTURING METHOD FOR ELECTRONIC  
5 COMPONENT-MOUNTED COMPLETED PRODUCT WITH THE ELECTRONIC  
COMPONENT-MOUNTED COMPONENT, AND ELECTRONIC COMPONENT-  
MOUNTED COMPLETED PRODUCT

### BACKGROUND OF THE INVENTION

10 The present invention relates to a manufacturing  
method for electronic component-mounted components to  
manufacture electronic component-mounted components by  
mounting electronic components such as semiconductor  
elements to a base, a manufacturing method for electronic  
15 component-mounted completed products with the electronic  
component-mounted components, and electronic component-  
mounted completed products with the electronic component-  
mounted components. The electronic component-mounted  
completed product with the electronic component-mounted  
20 components corresponds to stack modules, memory cards, non-  
contact IC cards and the like.

A conventional manufacturing method for an  
electronic component-mounted completed product which has,  
for example, a plurality of semiconductor elements,  
25 capacitors, resistors and the like passive components

mounted on one carrier substrate will be described below with reference to Figs. 11 and 12.

Conventionally, in a CSP (chip size package), an MCM (multi chip module) or a memory module having semiconductor elements, electronic components and the like passive components mounted ~~thereat~~ thereon, a mounting method has been employed for the semiconductor elements, by which the semiconductor elements are pressed with heat in contact onto the carrier substrate via a conductive adhesive or a conductive sheet. For the electronic components, a method has been employed by which the electronic components are mounted ~~at~~ in a predetermined circuit pattern by reflowing a solder paste printed in the predetermined circuit pattern on the carrier substrate.

More specifically, as shown in Fig. 11, projection-shaped electrodes 2 formed at electrode pads 1a of a semiconductor element 1 are electrically connected via an anisotropic conductive adhesive 15 to electrodes 3 on a carrier substrate 6. A sealing material 5 is injected and hardened between the semiconductor element 1 and the carrier substrate 6 so as to improve the jointing strength therebetween. At the opposite side ~~to~~ of a mounting face of the semiconductor element 1, electrodes 4 of the carrier substrate 6 and predetermined electrodes 8 of a motherboard 11 are connected with each other via a solder paste 7,

whereby the carrier substrate 6 is connected to the motherboard 11. To the electrodes 8 of the motherboard 11 are connected electrodes 10 of an electronic component 9 via the solder paste 7.

5           ~~A reference~~ Reference numeral 13 ~~is~~ denotes a through hole for electrically connecting the electrode 8 on a front face of the motherboard 11 to a circuit pattern 12 at a rear face of the motherboard 11. The through hole 13 is unnecessary in the case of a product without the circuit  
10           pattern 12.

          A memory module 14 as an example of the electronic component-mounted completed product with the electronic component-mounted components ~~is~~ formed in the above configuration.

15           As shown in Fig. 12, in a manufacturing process for the memory module 14, the solder paste 7 is applied by printing onto predetermined electrodes 8 on the motherboard 11 in a first step (denoted by "S" in the drawing) ~~1-first~~. Printing the solder paste 7 is normally carried out by  
20           screen printing. In a next step 2, the carrier substrate 6 with the semiconductor element 1 loaded and the electronic component 9 are registered onto the solder paste 7 formed by the printing respectively. In a succeeding step 3, the carrier substrate 6 with the semiconductor element ~~1-loaded~~,  
25           and the motherboard 11 with the electronic component 9

~~mounted~~ are passed through a reflow furnace to melt the solder paste 7. The solder paste is then ~~hardened then~~.

The memory module 14 as the electronic component-mounted completed product is manufactured in the manner as above (for instance, with reference to a ~~non-patent non-~~  
5 patent document 1: "Board Reliability of Ceramic CSP by Various Kinds of Solder Material" by Satoh, et al. at a symposium on "Microjoints and Assembly Technology in Electronics" on February 4-5, 2002, on page 133.)

10 The above-described conventional manufacturing method for the electronic component-mounted completed product with the electronic component-mounted components, and the configuration of the MCM or memory module as the electronic component-mounted completed product manufactured  
15 by the manufacturing method have the following problems that have yet to be solved.

Since electronic components such as the CSP are loaded on the motherboard 11, the module is increased in size in a thickness direction and thus cannot respond to  
20 the latest need for products to be thinned. The module is prone to be subject to effects of bending because of ~~this~~ the increased thickness increase and is difficult to be made flexible and applicable to a surface or the like shape. In addition, the motherboard 11 necessitates a region for  
25 loading the electronic component 9 and the carrier

substrate 6. Consequently, the number of electronic components loadable on one motherboard 11 and a region for forming the circuit pattern are determined by ~~a~~the size of the motherboard 11, which hinders efforts to meet the recent need of miniaturization of the motherboard 11.

Furthermore, since the semiconductor element 1 and the solder paste 7 are directly exposed to the atmosphere, oxidation takes place when the element and the solder paste are used under a high-temperature and high-humidity environment, often resulting in an electric short circuit, imperfect contact, a decrease in jointing strength ~~decrease~~ and the like. Also because of the uneven temperature in the reflow furnace, the motherboard 11 cannot be made large-size. The productivity is poor although a batch process is a mainstream.

#### SUMMARY OF THE INVENTION

The present invention has been devised to solve the above problems, and an object of the present invention is to provide a high-quality, high-productivity and inexpensive manufacturing method for electronic component-mounted components, a manufacturing method for electronic component-mounted completed products with the electronic component-mounted components, and electronic component-mounted completed products.

In accomplishing the object, according to a first aspect of the present invention, there is provided a manufacturing method for electronic component-mounted components, which comprises:

- 5           embedding an electronic component into a base;
- removing the base by carrying out at least one treatment of electrical discharge machining, laser beam machining, ion beam machining and electron beam machining to a machining face of the base, and thereby exposing
- 10          electrodes of the embedded electronic component; and
- forming a circuit pattern in contact with the exposed electrodes.

The method of the first aspect may be designed so that the method further comprises:

- 15          forming a through hole to penetrate the machining face and a rear face opposite to the machining face while carrying out the treatment to the base, and
- while forming the circuit pattern, forming an electric connection between the machining face and the rear
- 20          face via the through hole by at least one of conductive sputtering, vapor deposition and filling with a conductive material.

- The method of the first aspect may be designed so
- 25          that the electrodes of the electronic component have

projecting electrodes, and the exposing operation after the embedding into the base is to expose the projecting electrodes.

5           The method of the first aspect may be designed so that the circuit pattern forming operation forms at least one of a conductor routing, a metal thin film capacitor, a coil and a resistance in contact with the exposed electrodes by any one of plating, ion plating, sputtering  
10 and vapor deposition.

          The method of the first aspect may be designed so that the circuit pattern forming operation forms the circuit pattern by printing a solder paste or conductive  
15 adhesive on the exposed electrodes, then heating and hardening the solder paste or conductive adhesive.

          The method of the first aspect may be designed so that embedding the electronic component into the base is  
20 carried out ~~to~~ with a plurality of electronic components in the same process, and after the circuit pattern is formed, the base is cut so as to correspond to the respective electronic component-mounted components.

25           The method of the first aspect may be designed so



that embedding the electronic components into the base is carried out by heat press, the base is a thermoplastic sheet formed of any one of polyvinyl chloride, polycarbonate, acrylonitrile butadiene styrene, thermoplastic polyimide and polyethylene terephthalate and has a thickness of 0.010-2.000mm,~~a.~~ A glass transition point of the base is not lower than 333K and not higher than 423K,~~the.~~ The electronic component has a thickness that is smaller than that of the base, electrodes of the electronic component have a height of 0.0005-0.1mm, and the base at the heat press time is set to be at a temperature higher by 50K or more than the glass transition point and not higher than 473K.

According to a second aspect of the present invention, there is provided a manufacturing method for electronic component-mounted completed products, which comprises:

manufacturing electronic component-mounted components by a manufacturing method for electronic component-mounted components;

stacking the electronic component-mounted components or a base of the electronic component-mounted components in a thickness direction of the base after the manufacturing operation; and

executing a laminating process after the stacking,  
the manufacturing method for electronic  
component-mounted components including:

5 embedding an electronic component into the base,  
removing the base by carrying out at least one  
treatment of electrical discharge machining, laser beam  
machining, ion beam machining and electron beam machining  
to a machining face of the base, and thereby exposing  
electrodes of the embedded electronic component, and  
10 forming a circuit pattern in contact with the  
exposed electrodes.

According to a third aspect of the present  
invention, there is provided an electronic component-  
15 mounted completed product manufactured by a manufacturing  
method for electronic component-mounted completed products,  
the manufacturing method comprising:

manufacturing electronic component-mounted  
components by a manufacturing method for electronic  
20 component-mounted components;

stacking the electronic component-mounted  
components or a base of the electronic component-mounted  
components in a thickness direction of the base after the  
manufacturing operation; and

25 executing a laminating process after the stacking,

the manufacturing method for electronic component-mounted components including:

embedding an electronic component into the base,  
removing the base by carrying out at least one  
5 treatment of electrical discharge machining, laser beam  
machining, ion beam machining and electron beam machining  
to a machining face of the base, and thereby exposing  
electrodes of the embedded electronic component, and

forming a circuit pattern in contact with the  
10 exposed electrodes.

According to the manufacturing method for  
electronic component-mounted components of the first aspect,  
the manufacturing method for electronic component-mounted  
15 completed products of the second aspect, and the electronic  
component-mounted completed products of the third aspect of  
the present invention, the electronic component is embedded  
in the base, and therefore the thickness of the electronic  
component-mounted component can be ~~thinned~~ reduced. The  
20 electronic component-mounted component is rendered more  
flexible than in the conventional art because of the  
thinning and can hence be used at a curved surface or at a  
place where a bending operation is executed. Moreover,  
since the electronic component is embedded, a region for  
25 forming a film at the base surface and for forming the

circuit pattern is increased as compared with the conventional art, enabling the electronic component-mounted component to be highly functional and small in size. Additionally, since the electrical discharge machining, laser beam machining or the like is carried out so as to correspondingly to the electrodes of the embedded electronic component to expose the electrodes, the electrodes can be exposed in a shorter period of time than in the conventional art and through a local treatment, ~~whereby damages~~ and thereby damage to the base ~~are~~ is reduced. Hence the present invention can provide ~~the~~ a high-quality, high-productivity and inexpensive manufacturing method for electronic component-mounted components, a manufacturing method for electronic component-mounted completed products, and electronic component-mounted completed products as described above.

#### BRIEF DESCRIPTION OF THE DRAWINGS

These and other aspects and features of the present invention will become clear from the following description taken in conjunction with the preferred embodiments thereof with reference to the accompanying drawings, in which:

Fig. 1 is a sectional view of an electronic component-mounted component constructed in accordance with

an embodiment of the present ~~invention,~~invention;

Fig. 2 is a sectional view of an electronic component-mounted completed product ~~in a different~~  
constructed in accordance with another embodiment of the  
5 present ~~invention,~~invention;

Fig. 3 is a diagram explanatory of a manufacturing process for the electronic component-mounted component shown in ~~Fig. 1,~~Fig. 1;

Fig. 4 is a diagram explanatory of the  
10 manufacturing process for the electronic component-mounted component of Fig. 1 and showing a state ~~with~~in which an electronic component is embedded in a ~~base,~~base;

Fig. 5 is a diagram explanatory of the manufacturing process for the electronic component-mounted  
15 component of Fig. 1 and explanatory of a process of exposing ~~electrodes,~~electrodes;

Fig. 6 is a diagram explanatory of the manufacturing process for the electronic component-mounted component of Fig. 1 and showing a state ~~with~~in which  
20 electrodes ~~exposed,~~are exposed;

Fig. 7 is a sectional view ~~in~~of a modified example of the electronic component-mounted component shown in ~~Fig. 1,~~Fig. 1;

Fig. 8 is a diagram showing a state ~~with~~in which  
25 a plurality of the electronic component-mounted components

of Fig. 7 are formed at one base, base;

Fig. 9 is a diagram explanatory of a manufacturing method for the electronic component-mounted completed product shown in ~~Fig. 2,~~ Fig. 2;

5 Fig. 10 is a diagram explanatory of the configuration of a manufacturing apparatus for manufacturing the electronic component-mounted component of ~~Fig. 1,~~ Fig. 1;

Fig. 11 is a sectional view of a conventional electronic component-mounted ~~component,~~ component; and

Fig. 12 is a flow chart showing a conventional manufacturing process for the electronic component-mounted component.

## 15 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Before the description of the present invention proceeds, it is to be noted that like parts are designated by like reference numerals throughout the accompanying drawings.

20

A manufacturing method for electronic component-mounted components, a manufacturing method for electronic component-mounted completed products with the electronic component-mounted components, and electronic component-mounted  
25 mounted completed products manufactured by the

manufacturing method for electronic component-mounted completed products as embodiments of the present invention will be described below with reference to the drawings. Like parts are designated by like reference numerals throughout the drawings. Semiconductor elements, chip components as rectangular passive elements, cylindrical elements or the like, etc. correspond to one example of the electronic components included in the electronic component-mounted components.

10           An electronic component-mounted component 101 shown in Fig. 1 has a semiconductor element 111 and a passive element 113 embedded in a base 115. A circuit pattern 119 of the electronic component-mounted component 101 is formed on a machining face 115a of the base 115 after the base 115 is removed to expose respective electrodes 112 and 113a of the semiconductor element 111 and the passive element 113.

20           An electronic component-mounted completed product 105 shown in Fig. 2 has a structure in which the electronic component-mounted component 101 and an electronic component-mounted component 102 similar to the electronic component-mounted component 101 are stacked in two stages along a thickness direction of these electronic component-mounted components 101 and 102, and then laminated by sheet-shaped protecting materials 123 and 124.

A manufacturing method for the electronic component-mounted components 101 and 102, and the electronic component-mounted completed product 105 ~~constituted~~ constructed as above will be ~~depicted~~ described below.

First embodiment:

A manufacturing method for the electronic component-mounted component 101 will be described in the first place.

A process of mounting the semiconductor element 111 and the passive element 113 as electronic components into the base 115 includes a process of embedding the electronic components in the sheet-shaped base 115, a process of exposing electrodes 112 and 113a of the electronic components from the base 115, and a process of forming the circuit pattern 119 electrically connectible to the exposed electrodes 112 and 113a. The description here exemplifies the case of forming a sheet module having the semiconductor element 111 and the passive element 113 embedded in a thermoplastic sheet base as an example of the base 115.

The thermoplastic sheet base 115 is preferably, for example, polyethylene terephthalate, polyvinyl chloride, polycarbonate, acrylonitrile butadiene styrene, thermoplastic polyimide or the like having electrical



insulating properties with a thickness of  $10\mu\text{m}$ - $2.000\text{mm}$ . The thickness of the thermoplastic sheet base 115 is preferably larger than that of the semiconductor element 111 and the passive element 113 to be embedded, and a height of the electrode 112 of the semiconductor element 111 is preferably  $0.0005$ - $0.1\text{mm}$ . Moreover, a glass transition point of the thermoplastic sheet base 115 is preferably not lower than  $333\text{K}$  and not higher than  $423\text{K}$ . A temperature of the thermoplastic sheet base 115 at a heat press operation to be described later is preferably higher than the glass transition point by  $50\text{K}$  or more and not higher than  $473\text{K}$ .

Figs. 3 and 4 show sectional views of an example of the process of embedding the semiconductor element 111 and the rectangular passive element 113 into the thermoplastic sheet base 115. A method for embedding electronic components into the sheet base 115 is not limited to the illustrated one.

Projecting electrodes 112 are formed by known plating, stud bump bonding or the like manner to pads 111a of the semiconductor element 111. Moreover, a leveling process is carried out to the formed projecting electrodes 112, so that the projecting electrodes 112 are ~~unifor~~uniform in height. The leveling process may be omitted.

Fig. 3 is a diagram showing a state before the

electronic components 111 and 113 are embedded in the thermoplastic sheet base 115. The thermoplastic sheet base 115 is laid on a heating stage 117 heatable by a heater 1171. The semiconductor element 111 and the rectangular passive element 113 with electrodes 113a are placed on the thermoplastic sheet base 115. Further, a press tool 116 which can be moved in a thickness direction 171 of the thermoplastic sheet base 115 by a drive unit 1161 and is heated by a heater 1162 is arranged in contact with the semiconductor element 111 and the rectangular passive element 113. A loading face 117a for the thermoplastic sheet base 115 on the heating stage 117, and a contact face 116a of the press tool 116 to the electronic components are formed of glass, stainless, a ceramic, Teflon (registered trademark) or the like to enhance a fluid velocity of the thermoplastic sheet base 115 in the vicinity of the electrodes 112 and 113a and are preferably flat and rigid.

Although not shown in the drawings, a releasing material is preferably used to prevent the thermoplastic sheet base 115 from melting and adhering to the press tool 116 when the press tool 116 heats and presses the semiconductor element 111 and the passive element 113. The releasing material is preferably, e.g., glass, a ceramic, paper, Teflon (registered trademark) or the like. For example, a Teflon (registered trademark) sheet of a

thickness 50-100 $\mu$ m is preferably arranged between the semiconductor element 111 and the press tool 116 in the case where the semiconductor element 111 of a thickness of 180 $\mu$ m is to be embedded in the thermoplastic sheet base 115 formed of polyester terephthalate ~~of~~ and having a thickness of 200 $\mu$ m.

Although the press tool 116 is moved while the heating stage 117 is fixed in the instant example, the operation is not limited to this and a structure in which the heating stage 117 and the press tool 116 can move relatively in the thickness direction 171 is adoptable.

The semiconductor element 111 and the passive element 113 are pressed into the thermoplastic sheet base 115 by heating the press tool 116 and at the same time moving the press tool 116 by the drive unit 1161 towards the heating stage 117 with a load applied. At this time, while the thermoplastic sheet base 115, near the semiconductor element 111 and the rectangular passive element 113, becomes a viscous fluid and is being discharged to the periphery, the semiconductor element 111 and the rectangular passive element 113 are embedded in the thermoplastic sheet base 115 as indicated in Fig. 4.

A temperature control for the thermoplastic sheet base 115 is vital in the ~~embedding~~ embedding operation. If the electronic components 111 and 113 and the thermoplastic

sheet base 115 have ~~too low~~ temperatures that are too low,  
the viscosity of the thermoplastic sheet base 115 increases  
so as to cause an increase of a distance between the  
machining face of the thermoplastic sheet base 115 and each  
5 of electrodes 112 and 113a, whereby the thermoplastic sheet  
base 115 is blocked off from entering around the periphery  
of the electronic components 111 and 113. To the contrary,  
if the thermoplastic sheet base 115 is too high in the  
temperature, the thermoplastic sheet base 115 is increased  
10 in its fluidity and easily catches bubbles, and possibly  
the electronic components 111 and 113 even penetrate the  
thermoplastic sheet base 115.

As such, in the case, for instance, where the □  
2-6mm and 0.180mm-thick semiconductor element 111 having 4-  
15 50 gold electrodes 112 of a diameter 80μm and a height 40-  
60μm is to be embedded in the thermoplastic sheet base 115  
formed of terephthalate of a thickness 0.2mm, preferably,  
the temperature of the thermoplastic sheet base 115 ~~at~~  
during the embedding operation is ~~made~~ 150-170°C, the load  
20 by the press tool 116 is approximately 400-500N, and a  
pressing period of time is 20-150s.

After the above embedding operation, the drive  
unit 1161 moves up the press tool 116. The thermoplastic  
sheet base 115 having the semiconductor element 111 and the  
25 rectangular passive element 113 embedded is separated from

the heating stage 117 and cooled to a—room temperature. The thermoplastic sheet base 115 hardens again ~~by~~ due to the cooling. The projecting electrodes 112 and 113a are not yet exposed at the machining face 115a of the thermoplastic sheet base 115 at this time, or electrode surfaces are slightly covered with the gelled thermoplastic sheet base 115 even when the electrodes are exposed once. For instance, the distance in the thickness direction 171 from the electrode 112, 113a to the machining face 115a of the thermoplastic sheet base 115 is 100 $\mu$ m at maximum in the example. Consequently an electric connection between element electrodes cannot be obtained in this state ~~as it is~~ is.

~~For obtaining~~ In order to obtain the electric connection, in the present embodiment, the thermoplastic sheet base 115 which covers surfaces of the electrodes 112 and 113a is removed by at least one treatment of electric discharge machining, laser beam machining, ion beam machining, and electron beam machining. The laser beam machining is adopted here in the example. More specifically, a sheet module 1010 having the semiconductor element 111 and the rectangular passive element 113 embedded in the thermoplastic sheet base 115 as shown in Fig. 4 is inverted, and is placed on a stage 172 for laser beam machining so that the machining face 115a of the

thermoplastic sheet base 115 covering the surfaces of the electrodes 112 and 113a and a laser generator 173 for generating laser beams are opposite to each other, as shown in Fig. 5. Then, for removing coating parts 115b of the thermoplastic sheet base 115 present on the electrodes 112 and 113a, a laser beam 174 is applied from the laser generator 173 for a fixed period of time while being focused on the machining face 115a corresponding to the coating parts 115b. The coating parts 115b are melted, further vaporized and removed by the exposure, whereby the electrodes 112 and 113a are exposed to the outside. The laser used is preferably a ruby laser, a glass laser, an Ar laser, a YAG laser, a CO<sub>2</sub> laser, an excimer laser or the like. Preferably, ~~a~~the laser power density is  $10^{7-8}$  W/cm<sup>2</sup> and ~~an~~the application period of time is  $10^{(-3)-(-5)}$ s.

Since the electrodes 112 and the like are coated with the coating parts 115b before the laser beam machining as described above, the electrodes 112 and the like, a pattern position, etc. are first recognized by letting an infrared ray passes through in order to position an exposure position of the laser beam 174 to the electrodes 112 and the like. The recognition operation enables setting the exposure position with a high accuracy of, e.g.,  $\pm 5\mu\text{m}$ .

The sheet module 1010 in which the electrodes 112

and 113a are exposed at openings 115c formed by removing the coating parts 115b by the above laser beam machining is thus manufactured as shown in Fig. 6.

In the above laser beam machining, for instance,  
5 the openings 115c of a diameter of 80-100 $\mu$ m and a depth of 40 $\mu$ m are preferably formed in the periphery of the electrodes 112 for the module which has the 180 $\mu$ m-thick semiconductor element 111 with the 40 $\mu$ m-high and 80 $\mu$ m-pedestal diameter projecting electrodes 112 of gold  
10 embedded in the thermoplastic sheet base 115 formed of, e.g., polyester terephthalate or the like in a film thickness of 250 $\mu$ m.

After the openings 115c are formed as above, as shown in Fig. 1, the circuit pattern 119 is formed in  
15 contact with the exposed electrodes 112 and 113a. Known sputtering, vapor deposition, ion plating, plating, printing a conductive adhesive or the like method can be used as a forming method for the circuit pattern 119. The projection-shaped electrode 112 is shaped like a mountain and has a large surface area at the opening 115c, and is  
20 accordingly easy to catch the sputter, vapor deposition particles or conductive adhesive. Thus, a contact area ~~to~~ a-for the circuit pattern forming material is made large, so that a connection resistance between the projection-shaped electrode 112 and the circuit pattern 119 is  
25

advantageously reduced.

In forming the circuit pattern 119, for example, by the aforementioned sputtering, a high voltage is impressed under a high vacuum to generate plasma with the use of, e.g., gold, silver, copper, aluminum, chromium, nickel, palladium or the like as a target material, thereby sputtering the target material and piling the target material particles via a mask onto the thermoplastic sheet base 115. A gas of Ar, O<sub>2</sub>, HF or the like is preferably introduced at the sputtering operation.

Alternatively, the circuit pattern 119 may be formed with the use of the known photolithography after the entire face of the thermoplastic sheet base 115 is subjected to plating, vapor deposition or the like.

The circuit pattern 119 may also be formed by printing a conductive adhesive with mask, heating and then hardening the conductive adhesive. For instance, when a silver paste is used as the conductive adhesive, the printing is preferably carried out by a flat squeegee by 5mm/s with the use of a mask of 250mesh/inch, an emulsion thickness 0.030mm and a mask thickness 0.100mm. After the printing operation, the thermoplastic sheet base is put in a curing furnace to harden the conductive adhesive, whereby the circuit pattern 119 is formed. The conductive adhesive is preferably ~~the~~ a silver paste, a copper paste, a silver



palladium paste or the like.

As described hereinabove, according to the machining method of exposing the electrodes 112 and 113a with the utilization of laser beams, (1) machining is enabled in a considerably short period of time because the laser beam machining takes only lms or shorter per one machining spot as compared with the case in which the base is cut by dry etching or the like method, and (2) the base is less damaged because the machining is local heat input machining, as well as the other advantages exhibited.

Second embodiment:

Fig. 7 shows a sheet module corresponding to the electronic component-mounted component 102 which has a through hole 118 ~~as a hole~~ penetrating the machining face 115a of the thermoplastic sheet base 115 and a rear face 115d opposite to the machining face 115a, and also a thin film capacitor 120 as contrasted with the electronic component-mounted component 101 shown in Fig. 1. The through hole 118 is formed by boring the thermoplastic sheet base 115 in its thickness direction by a laser, an ion beam or an electron beam. An inner peripheral face or inside of the through hole 118 is provided with a conductive material concurrently when the circuit pattern 119 is formed. Accordingly, an electric connection between the machining face 115a and the rear face 115d is obtained

via the through hole 118 by at least one treatment of  
conductive sputtering, vapor deposition, filling a  
conductive material, and the like. A diameter of the  
through hole 118 is made, for instance, 0.1mm. The thin  
5 film capacitor 120 is formed by sputtering or vapor  
depositing two kinds of conductive films to cover the  
electrodes 112 via a dielectric film. A spiral wiring  
pattern may be formed to form a coil as a part of the  
circuit pattern 119 as illustrated. The circuit pattern  
10 119 may have a thin film resistance formed thereto.

As shown in Fig. 8, a plurality of, for example,  
9—nine semiconductor elements 111 can be embedded in one  
thermoplastic sheet base 115, whereby 9nine of the  
electronic component-mounted components 102 can be  
15 manufactured at a single time. In this case, 9—nine  
semiconductor elements 111 can be embedded altogether in  
the same process. The exposure process of electrodes 112  
and the circuit pattern formation process ~~to~~for one  
thermoplastic sheet base 115 are carried out by the earlier  
20 depicted corresponding methods respectively. After 9nine  
electronic component-mounted components 102 are formed, the  
thermoplastic sheet base is cut in order to separate  
electronic component-mounted components 102 with the use of  
a dicing machine, a laser or the like.

25 Needless to say, the number of electronic

component-mounted components 102 to be formed at ~~from~~ one  
thermoplastic sheet base 115 is not restricted to the above  
9 nine.

Third embodiment:

5           The electronic component-mounted component 101 in  
the above first embodiment and the electronic component-  
mounted component 102 in the above second embodiment are  
stacked in the thickness direction ~~of them~~ thereof and  
moreover laminated by two sheet-shaped protecting materials  
10   123 and 124 to cover the electronic component-mounted  
components 101 and 102, whereby the electronic component-  
mounted completed product 105 as shown in Fig. 2 can be  
manufactured. The electronic component-mounted-component  
102 included in the electronic component-mounted completed  
15   product 105 of this third embodiment has no circuit pattern  
119 formed at the rear face 115d. The electronic  
component-mounted component 101 and the electronic  
component-mounted component 102 are registered with each  
other so that the through hole 118 formed in the electronic  
20   component-mounted component 102 is electrically connected  
to the circuit pattern 119 of the electronic component-  
mounted component 101. The electronic component-mounted  
component 101 and the electronic component-mounted  
component 102 are held between the protecting materials 123  
25   and 124 along the thickness direction 171 and then

laminated by a rolling press 127 with two rollers 125 and a presser 126 for moving the rollers 125 in the thickness direction 171.

5       The electronic component-mounted completed product 105 formed in this manner is prevented from exposure of the electronic components 111 and 113 to the atmosphere and is accordingly made resistant to oxidation or migration. At the same time, the thermoplastic sheet base 115 and the like are also prevented from abrasion.

10       The electronic component-mounted completed product can be formed into a thin card to be made portable. The number of electronic component-mounted components to stack is not limited to the above 2two and can be 3three or more.

15       A manufacturing apparatus for carrying out processes up to the exposure of electrodes 112 and 113a for the electronic component-mounted component in each of the foregoing embodiments will be depicted here.

20       An electronic component-mounted component manufacturing apparatus 201 shown in Fig. 10 comprises a base supply device 211 for supplying the thermoplastic sheet base 115, an electronic component supply device 221 for supplying the semiconductor elements 111 and the passive elements 113, a recognizing device 231, a machining device 241, a transfer device 251, and a controller 261 for

25       controlling ~~driving~~ the operation of each of these

constituent parts.

The machining device 241 includes the heating stage 117, the press tool 116 and the like discussed with reference to Figs. 3 and 4, and the laser generator 173  
5 discussed with reference to Fig. 5.

The transfer device 251 has a transfer mechanism 254, a component holding mechanism 255, a semiconductor element inverting device 252, and a sheet material inverting device 253, which carries out a transfer  
10 operation by the transfer mechanism 254 for the thermoplastic sheet base 115 from the base supply device 211 to the heating stage 117 and from the heating stage 117 to the stage 172 for laser beam machining as well as an inverting operation for the semiconductor elements 111 by  
15 the semiconductor element inverting device 252 and an inverting operation for the thermoplastic sheet base 115 with embedded electronic components by the sheet material inverting device 253 installed in the middle of a transfer path from the heating stage 117 to the stage 172 for laser  
20 beam machining. The transfer of the thermoplastic sheet base 115 by the transfer mechanism 254 is executed by transferring a tray on which the thermoplastic sheet base 115 is placed. The semiconductor element inverting device 252 and the sheet material inverting device 253 have  
25 driving devices 2521 and 2531 respectively.

The component holding mechanism 255 transfers semiconductor elements 111 from the electronic component supply device 221 to the semiconductor element inverting device 252 and from the semiconductor element inverting device 252 to the heating stage 117.

The recognizing device 231 has a camera 2311 for semiconductor elements which recognizes the semiconductor element 111 arranged at the electronic component supply device 251 and held by the component holding mechanism 255 and which images the thermoplastic sheet base 115 placed on the heating stage 117, and a camera 2312 for laser beam machining which recognizes a machining position disposed above the stage 172 to be treated by the laser generator 173.

Operations in the electronic component-mounted component manufacturing apparatus 201 constituted as above will be described hereinafter.

In the first place, a plurality of sheets of the thermoplastic sheet base 115 to embed semiconductor elements 111 are prepared at the base supply device 211 and sequentially transferred onto the heating stage 117. The heating stage 117 and the press tool 116 may be used under any of the atmospheric pressure and vacuum pressure. Preferably, the heating stage 117 and the press tool 116 are equipped with a multi stage mechanism so that a

plurality of sheets can be heat pressed while overlapping in the thickness direction 171, a rotary stage mechanism configured so that the thermoplastic sheet base 115 is sequentially transferred to each of a plurality of stages  
5 divided by functions such as preheating, practical heating and cooling and arranged in a circumferential form, or is accompanied with a temperature profile controller for carrying out a temperature control at a heat press operation and the like.

10               At the electronic component supply device 221, semiconductor elements 111 having projecting electrodes 112 preliminarily formed at electrode pads thereof are regularly stored in trays with electrode faces turned upside. The trays are piled in a multi stage. However, a  
15 storing method for the semiconductor elements 111 is not limited to this and, the semiconductor elements of wafers may be stored as they are.

              Secondly, characteristic points of the semiconductor elements 111 at formation faces of projecting  
20 electrodes 112, circuit patterns, outlines of the semiconductor elements 111 or the like are recognized by the camera 2311 for semiconductor elements, thereby selecting a desired semiconductor element 111 to be embedded. Then, the selected semiconductor element 111 is  
25 sucked and held by the component holding mechanism 255

having a suction function, and placed on the semiconductor element inverting device 252. After the rear face of the semiconductor element 111 is made upside by rotating the semiconductor element inverting device 252, the  
5 semiconductor element 111 is sucked and held again at the rear face by the component holding mechanism 255.

In the meantime, an embedding position at the thermoplastic sheet base 115 on the heating stage 117 is recognized by the camera 2311 for semiconductor elements,  
10 and then the inverted semiconductor element 111 is placed on the thermoplastic sheet base 115 on the heating stage 117.

Thereafter, the press tool 116 is moved to heat press the thermoplastic sheet base while a load is applied  
15 to the sheet base. The driving unit 1161 of the press tool 116 shown in Fig. 3 is preferably controlled by the controller 261. The controller 261 controls a start position where the press tool 116 starts ~~coming~~coming into contact with the semiconductor element 111, a pressing  
20 end position, a descend velocity, an ascend velocity and the like.

After the semiconductor element 111 is embedded in the thermoplastic sheet base 115, and the sheet module after the embedding is cooled, the sheet module 1010 is  
25 transferred onto the sheet material inverting device 253



and inverted by the sheet material inverting device 253.  
The sheet module 1010 is subsequently placed on the stage  
172 for laser beam machining of a laser beam machining unit.

After the laser beam machining position is  
5 recognized by the camera 2312 for laser beam machining, the  
laser beam 174 is applied by the laser generator 173 to  
illuminate the machining face 115a of the thermoplastic  
sheet base 115 until the electrodes 112 and 113a are  
exposed. A machining period of time, a laser output and  
10 the like of the laser generator 173 are preferably made  
settable.

The sheet module 1010 with the electrodes 112 and  
113a exposed is formed by the above operation. The sheet  
module is transferred by a transfer device not illustrated  
15 from the stage 172 for laser beam machining to a forming  
process for the circuit pattern 119 in a next stage or the  
like.

Although the present invention has been fully  
20 described in connection with the preferred embodiments  
thereof with reference to the accompanying drawings, it is  
to be noted that various changes and modifications are  
apparent to those skilled in the art. Such changes and  
modifications are to be understood as included within the  
25 scope of the present invention as defined by the appended

claims unless they depart therefrom.

# ABSTRACT

A semiconductor element (111) with electrodes (112), and a passive element (113) with electrodes (113a) are embedded in a thermoplastic sheet base (115), which is  
5 then subjected to laser beam machining, electron beam machining or ion beam machining to expose electrodes (112 and 113a). Thereafter, a circuit pattern (119) is formed by formation of a thin film or printing of a conductive adhesive. ~~Because of exposing~~ Exposing the electrodes by  
10 laser beam machining or the like ~~manner as above, the exposure~~ can be carried out in a short period of time and also by a local treatment, thereby reducing damages to the base. ~~The high quality, high productivity and inexpensive manufacturing method for electronic component-mounted~~  
15 ~~components, manufacturing method for electronic component-mounted completed products, and electronic component-mounted completed products can be provided accordingly.~~